


Chemical Resistance


Chemical resistance of PROCON® (PPS)



Chemical Resistance

Hydrolysis resistance of PROCON[®] (PPS)

PROCON[®] does not undergo hydrolysis even at high temperatures.



Flame Retardancy

LOI : Limited Oxygen Index

(The minimum oxygen concentration required to continue burning in air)

PROCON®LOI value of 34 indicates high flame retardancy.

