

# Spec

## VYLON® Solvent soluble type

	Grade	Form	Specific gravity (at30)	Tg	Molecular weight	Hydroxyl group value	Acid value	Features
				°C		KOHmg/g	KOHmg/g	
High Tg	200	Pellet	1.26	67	17,000	6	<2	Adhesion property, general purpose grade
	GK-360	Flake	1.24	56	16,000	7	5	Adhesion to PET, weatherability
Intermediate Tg	600	Pellet	1.25	47	16,000	7	<2	Intermediate Tg, general purpose grade
	GK-810	Flake	1.17	46	6,000	19	5	Solvent solubility, can overcoat
Low Tg	630	Sheet	1.2	7	23,000	5	<2	Flexibility, solution stability
	GK-680	Sheet	1.16	10	6,000	21	<2	Solvent solubility, can overcoat