

Spec

VYLON® Solvent insoluble type

	Grade	Form	Specific gravity (at30)	Tm	Molecular weight	Hydroxyl group value	Features
				°C		dPa · s/200°C	
High Tm	GA-1310	Pellet	1.29	179	20,000	1,500	Solvent resistance, fuel filter
Intermediate Tm	GM-400	Pellet	1.3	143	25,000	4,600	Dry cleaning resistance, fabric application
Low Tm	GM-920	Pellet	1.15	107	30,000	1,000	Adhesion property, moisture resistance

VYLON® Solvent soluble type

	Grade	Form	Specific gravity (at30)	Tm	Molecular weight	Hydroxyl group value	Features
				°C		dPa · s/200°C	
Extrusion performance	SI-173	Pellet	1.28	185	25,000	7,000	toughness