

# Spec

Grade	Form	Color	Specific gravity	Hardness Shore A	Tm °C	Tg °C	Melt Viscosity dPa · s/220°C	Features
GM-950-R02	Pellet	Black	1.14	90	190	-65	420	High Melting Point
GM-955-R02	Pellet	Black	1.05	70	160	-77	340	Low elasticity
GM-950-RF4	Pellet	Gray	1.19	94	182	-70	890	Flame Retardant
GM-955-RK20	Pellet	Black	1.03	70	160	-77	530	High adhesive strength Low elasticity
GM-960-RK40	Pellet	Black	1.04	86	160	-65	300	High adhesive strength High flow rate
GM-964-B01	Pellet	Natural	1.12	90	163	-65	1720	Cutting oil resistance Light visibility