


Grades

		Tenacity		Modulus		Elongation	Linear Density
		cN/dtex	g/d	cN/dtex	g/d	%	dtex
IZANAS®	SK60	31	35	1000	1130	4.0	22 - 1760
	SK71	38	43	1400	1590	3.9	440
	SK777	35	40	1200	1360	3.9	1760
	SK888	43	49	1500	1700	4.0	880, 1760
	SF600	26	29	800	910	4.4	55 - 1320
	SF700	40	45	1400	1590	4.2	55 - 440

Product Form

- Filament yarn
- Chopped fiber
- Staple fiber
- Cloth
- Nonwoven fabric
- Knitted fabric



Filament yarn

dtex	denier	SK60	SK71	SK777	SK888	SF600	SF700
22	20	*					
33	30	*					
44	40	*					
55	50	*				*	*
85	75	*				*	*
110	100	*				*	*
140	125	*				*	
165	150	*				*	*
220	200	*				*	*
275	250	*				*	
330	300	*				*	*
440	400	*	*			*	*
880	800	*			*	*	
1320	1200	*				*	
1760	1600	*		*	*		